

MTSCOMAXTECH

<https://www.mtscomaxtech.com>

**SPECIFICATION FOR WELDED NICKEL-
IRON-CHROMIUM ALLOY PIPE**



SB-514

(Identical with ASTM Specification B514-05(2019) except for the deletion of para. 5.1.6.)

Specification for Welded Nickel-Iron-Chromium Alloy Pipe

1. Scope

1.1 This specification covers nickel-iron-chromium alloys in the form of welded, cold-worked, and annealed pipe for general corrosive service and heat-resisting applications. These products are furnished in three alloys: UNS N08120, UNS N08800, and UNS N08810. Alloy UNS N08800 is employed normally in service temperatures up to and including 1100 °F (593 °C). Alloys UNS N08120 and UNS N08810 are employed normally in service temperatures above 1100 °F where resistance to creep and rupture is required, and are annealed to develop controlled grain size for optimum properties in this temperature range.

1.2 This specification covers outside diameter and nominal wall pipe shown in ANSI B36.19. Pipe having other dimensions may be furnished provided such pipe complies with all other requirements of the specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:

B775 Specification for General Requirements for Nickel and Nickel Alloy Welded Pipe
B899 Terminology Relating to Non-ferrous Metals and Alloys

2.2 ANSI Standard:

B36.19 Stainless Steel Pipe

3. Terminology

3.1 Terms defined in Terminology B899 shall apply unless defined otherwise in this standard.

4. General Requirement

4.1 Material furnished in accordance with this specification shall conform to the applicable requirements of the current edition of Specification B775 unless otherwise provided herein.

5. Ordering Information

5.1 Orders for material under this specification should include the following information:

5.1.1 Alloy name or UNS number.

5.1.2 ASTM designation and year of issue.

5.1.3 Condition (temper) (Table 1).

5.1.4 *Dimensions:*

5.1.4.1 Nominal pipe size or outside diameter and schedule number or nominal wall thickness.

5.1.4.2 Length (specific or random).

5.1.5 Quantity (feet or metres, or number of pieces).

5.1.6 DELETED

5.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished.

5.1.8 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of

TABLE 1 Mechanical Property Requirements

Alloy	Condition (Temper)	Tensile Strength, min, psi (MPa)	Yield Strength, 0.2 % Offset, min, psi (MPa)	Elongation in 2 in. or 50 mm, min, %
UNS N08120	annealed	90 000 (621)	40 000 (276)	30
UNS N08800	annealed	75 000 (520)	30 000 (207)	30
UNS N08810	annealed	65 000 (450)	25 000 (170)	30

manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

6. Materials and Manufacture

6.1 Pipe shall be made from flat-rolled alloy by an automatic welding process with no addition of filler metal. Subsequent to welding and prior to final solution treatment, the material shall be cold worked either in both weld and base metal or in weld metal only.

6.2 Pipe shall be furnished with a scale-free finish. When bright annealing is used, descaling is not necessary.

7. Chemical Composition

7.1 The material shall conform to the requirements as to chemical composition prescribed in Table 2.

7.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in Table 1 of Specification B775.

TABLE 2 Chemical Requirements

Element	Composition Limits, %	
	Alloy N08120	Alloys N08800 and N08810
Nickel	35.0 min	30.0 min
	39.0 max	35.0 max
Chromium	23.0 min	19.0 min
	27.0 max	23.0 max
Iron	remainder	39.5 min ^A
Manganese, max	1.5	1.5
Carbon	0.02 min	^B
	0.10 max	
Copper, max	0.50 max	0.75
Silicon, max	1.0	1.0
Sulfur, max	0.03	0.015
Aluminum	0.40 max	0.15 min
	...	0.60 max
Titanium	0.20 max	0.15 min
	...	0.60 max
Columbium	0.4 min	...
	0.9 max	...
Molybdenum	2.50 max	...
Phosphorus	0.040 max	...
Tungsten	2.50 max	...
Cobalt, max	3.0	...
Nitrogen	0.15 min	...
	0.30 max	...
Boron	0.010 max	...

^A Iron shall be determined arithmetically by difference.

^B Alloy UNS N08800: 0.10 max. Alloy UNS N08810: 0.05 to 0.10.

8. Mechanical and Other Requirements

8.1 *Mechanical Properties*—The material shall conform to the requirements for mechanical properties prescribed in Table 1.

8.2 *Grain Size*—A transverse sample representing the full-wall thickness of annealed alloys UNS N08120 and N08810 shall conform to an average grain size of ASTM No. 5 or coarser.

8.3 *Flattening Test*—Pipe shall be capable of withstanding, without cracking, flattening under a load applied gradually at room temperature until the distance between the platens is five times the wall thickness. The weld shall be positioned 90° from the direction of the applied flattening force.

8.4 *Annealing Temperature*—Alloy UNS N08120 shall be annealed at 2150 °F (1177 °C) minimum; alloy UNS N08810 shall be annealed at 2050 °F (1120 °C) minimum.

8.5 *Nondestructive Test Requirements:*

8.5.1 *Category 1*—Each piece of each lot shall be subject to one of the following four tests: hydrostatic, pneumatic (air underwater), eddy current, or ultrasonic.

8.5.2 *Category 2*—Each piece in each lot shall be subjected to a leak test and an electric test as follows:

8.5.2.1 *Leak Test*—Hydrostatic or pneumatic (air underwater).

8.5.2.2 *Electric Test*—Eddy current or ultrasonic.

8.6 The manufacturer shall have the option to test Category 1 or Category 2 and select the nondestructive test methods, if not specified by the purchaser.

8.7 *Transverse Guided Bend Test*—At the option of the pipe manufacturer, the transverse guided bend test may be substituted in lieu of the flattening test. Two bend specimens shall be taken transversely from pipe or the test specimens may be taken from a test plate of the same material and heat as pipe, which is attached to the end of the cylinder and welded as a prolongation of the pipe longitudinal seam. One test is required for each lot as defined in Specification B775.

9. Number of Tests

9.1 *Chemical Analysis*—One per lot.

9.2 *Mechanical Properties*—One test per lot.

9.3 *Flattening or Transverse Guided Bend Test*—One test per lot.

9.4 *Grain Size*—One test per lot.

9.5 *Nondestructive*—Each piece in each lot.

10. Keywords

10.1 UNS N08120; UNS N08800; UNS N08810; welded pipe