




## FROM MILL TO MARKET ALL AT MTSCO

Nickel Alloy · Austenitic · Duplex Steel

<https://www.mtscomaxtech.com>



ASTM B704 Standard Specification

# Standard Specification for Welded UNS N06625, UNS N06219 and UNS N08825 Alloy Tubes<sup>1</sup>

This standard is issued under the fixed designation B704; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers welded UNS N06625, UNS N06219 and UNS N08825 alloy boiler, heat exchanger, and condenser tubes for general corrosion resisting and low or high-temperature service.

1.2 This specification covers tubes  $\frac{1}{8}$  to 5 in. (3.18 to 127 mm), inclusive, in outside diameter and 0.015 to 0.500 in. (0.38 to 12.70 mm), inclusive, in wall thickness. Specification **B751** lists the dimensional requirements of these sizes. Tubes having other dimensions may be furnished provided such tubing complies with all other requirements of this specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**B751** Specification for General Requirements for Nickel and Nickel Alloy Welded Tube

**E8** Test Methods for Tension Testing of Metallic Materials

## 3. Ordering Information

3.1 Orders for material to this specification should include the following information:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **B02** on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee **B02.07** on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 1, 2014. Published October 2014. Originally approved in 1982. Last previous edition approved in 2009 as B704 – 03 (2009). DOI: 10.1520/B0704-03R14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 Quantity (feet or number of lengths),

3.1.2 UNS number,

3.1.3 Size (outside diameter, minimum or average wall thickness),

3.1.4 Length (random or specific),

3.1.5 Class, and

3.1.6 Grade if UNS N06625 is specified. If neither grade of N06625 is specified, grade 1 will be supplied.

3.1.7 ASTM designation.

3.1.8 *Product Analysis*—State if required.

3.1.9 *Certification*—State if a certification or a report of test results is required.

3.1.10 *Purchaser Inspection*—State which tests or inspections are to be witnessed, if any.

## 4. Materials and Manufacture

4.1 Tube shall be made from flat-rolled alloy by an automatic welding process with no addition or filler metal. Subsequent to welding and prior to final annealing, the material shall be cold-worked in either the weld metal only or both weld and base metal.

4.2 Tube shall be furnished with oxide removed. When bright annealing is used, descaling is not necessary.

## 5. Chemical Composition

5.1 The material shall conform to the composition limits specified in **Table 1**. One test is required for each lot as defined in Specification **B751**.

5.2 If a product analysis is performed, it shall meet the chemistry limits prescribed in **Table 1**, subject to the analysis tolerances of Specification **B751**.

## 6. Mechanical and Other Properties

6.1 *Mechanical Properties*—The material shall conform to the mechanical property requirements specified in **Table 2**. One test is required for each lot as defined in Specification **B751**.

6.2 *Flattening Test*—A flattening test shall be made on each end of one tube per lot. Superficial ruptures resulting from surface imperfections shall not be cause for rejection.

6.3 *Flange Test*—A flange test shall be made on each end of one tube per lot.

**TABLE 1 Chemical Requirements**

	Composition Limits, %		
	UNS N06625	UNS N06219	UNS N08825
Ni	58.0 min <sup>A</sup>	Bal	38.0–46.0
Cr	20.0–23.0	18.0-22.0	19.5–23.5
Fe	5.0 max	2.0-4.0	22.0 min <sup>A</sup>
Mo	8.0–10.0	7.0-9.0	2.5 3.5
Cb + Ta	3.15–4.15	...	...
C	0.10 max	0.05 max	0.05 max
Mn	0.50 max	0.50 max	1.0 max
Si	0.5 max	0.70-1.10	0.5 max
P	0.015 max	0.020 max	...
S	0.015 max	0.010 max	0.03 max
Al	0.4 max	0.50 max	0.2 max
Ti	0.40 max	0.50 max	0.6–1.2
Co (if determined)	1.0 max	1.0 max	...
Cu	...	0.50 max	1.5–3.0

<sup>A</sup> Element may be determined arithmetically by difference.

**6.4 Nondestructive Test Requirements:**

6.4.1 *Class 1*—Each piece in each lot shall be subject to one of the following four tests: hydrostatic, pneumatic (air underwater), eddy current, or ultrasonic.

6.4.2 *Class 2*—Each piece in each lot shall be subjected to a leak test and an electric test as follows:

6.4.2.1 *Leak Test*—Hydrostatic or pneumatic (air underwater).

6.4.2.2 *Electric Test*—Eddy current or ultrasonic.

6.5 The manufacturer shall have the option to test to Class 1 or 2 and select the nondestructive test methods, if not specified by the purchaser.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*

**TABLE 2 Mechanical Property Requirements**

Alloy	Grade	Tensile Strength	Yield Strength <sup>A</sup>	Elongation in 2 in. or 50 mm, min, %
		min, psi (MPa)	0.2 % Offset, min, psi (MPa)	
UNS N06625	1 (annealed)	120 000 (827)	60 000 (414)	30
UNS N06625	2 (solution annealed) <sup>B</sup>	100 000 (690)	40 000 (276)	30
UNS N06219	...	96 000 (660)	39 000 (270)	30
UNS N08825	...	85 000 (586)	35 000 (240)	30

<sup>A</sup> Yield strength shall be determined by the offset method at 0.2 % limiting permanent set in accordance with Test Methods E8.

<sup>B</sup> Solution annealed at 2000°F (1093°C) minimum, with or without subsequent stabilization anneal at 1800°F (982°C) minimum to increase resistance to sensitization.

**7. General Requirements**

7.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification B751 unless otherwise provided herein.

**8. Product Marking**

8.1 In addition to the requirements of Specification B751, UNS N06625 tubes shall be marked with grade information.

**9. Keywords**

9.1 UNS N06219; UNS N06625; UNS N08825; welded tube